DARVAN® 670

Dispersing Agent for Coatings and Construction



TECHNICAL DATA

DARVAN® 670 dispersing agent is highly effective in preventing the agglomeration or coalescence of suspended solids, liquids or gases in aqueous systems. **DARVAN 670** is used to prevent settling and to lower the viscosity of pigment slurries, to improve the stability of emulsions and to keep air bubbles from coalescing in processes such as froth floatation. **DARVAN 670** is an effective anionic dispersing agent for the preparation of dispersions of colored pigments, dyes, extender pigments, etc. It is effective for viscosity reduction of high solids dispersions of red iron oxide and similar pigments. **DARVAN 670** also act as secondary dispersing agents and emulsion stabilizers in emulsions of synthetic rubber products.

TYPICAL PROPERTIES

Chemical Classification	Sodium salt of poly-naphthalene sulfonic acid
Physical State	Amber powder
% Active	88% minimum
Density at 25°C	1.25 g/cc, 10.4 lbs/gal
pH (1% solution)	8 -10.5
Gardiner color (1% solution)	4 maximum
Moisture Content	8% maximum
Foaming tendency	None
Solubility	Readily soluble in hot or cold water
Recommended Use Level	1-3% based on weight of solids

CONTACT INFORMATION

For samples, product information and/or technical service please contact Vanderbilt Minerals, LLC or the Vanderbilt representative in your area:

Vanderbilt Minerals, LLC

33 Winfield Street, P.O. Box 5150 Norwalk, CT 06856-5150 P: (800) 562-2476 F: (203) 855-1220 www.vanderbiltminerals.com

DARVAN is a registered trademark of Vanderbilt Minerals, LLC

5/2020

Before using, read, understand and comply with the information and precautions in the Safety Data Sheets, label and other product literature. The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Minerals, LLC does not warrant the test be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent, trademark or copyright or to violate any federal, state or local law or regulation.