

Water-in-Oil Luxurious Makeup No. 332

		Wt.%
A	VEEGUM® Magnesium Aluminum Silicate	1.2
	Deionized Water	37.9
	Magnesium Sulfate	0.4
B	Talc	5.5
	Kaolin	1.5
	Titanium Dioxide	5.0
	Iron Oxides	3.0
C	Mineral Oil	15.0
	Hydrogenated Polyisobutylene (Parleam® ¹)	8.0
	Mineral Oil (and) Lanolin Alcohol (Vilvanolin™ L101 ²)	8.0
	Isopropyl Lanolate (and) Lecithin (Lanapene™ ³)	7.0
	Sorbitol, 70%	5.0
	Oleamide DEA (Schercomid™ ODA ²)	2.5
D	Preservative	q.s.

Procedure: Slowly add the VEEGUM® R to the water agitated at maximum available shear. Mix until fully hydrated. Add the Magnesium Sulfate and mix until smooth. Grind Part B and add to Part A, mixing until uniform. Add Parts A & B to Part C. Mix until uniform and smooth. Add Part D and mix until uniform.

RAW MATERIAL SUPPLIERS¹Rossow Cosmetics – USA, Matawan, NJ²Lubrizol Advanced Materials, Inc., Cleveland, OH³Lanaetex Products Inc., Elizabeth, NJ**TRADEMARKS**

VEEGUM is a registered trademark of Vanderbilt Minerals, LLC.

Lanapene is a trademark of Lanaetex Products Inc.

Parleam is a registered trademark of Etablissements B. Rossow et Cie.

Schercomid and Vilvanolin are trademarks of Lubrizol Advanced Materials, Inc.

Rev04/25/2013